



NewTech™ - CleverDeck™ Specifications

Board & Pack Size:

Width	Thickness	Length	Length per pack	Lin./m per pack	Weight per pack
86mm	23mm	5400mm	143	772.2	1780kg
138mm	23mm	5400mm	91	491.4	1880kg

Physical, Mechanical and Thermal Properties:

Test	ASTM	PSI	MPA
Tensile Strength	D638	1806	12.45
Bend Strength	D790	3084	21.26
Bend Modulus	D790	275181	1897.31
Flexural Strength	D6109	2781	19.17
Flexural Modulus	D6109	302032	2082.44
Nail Withdrawal	D1544	802	
Water Absorption	D1037	1.26%	
Density	D792	1.2 – 1.3 g/cm ³	
Shore D Hardness	GB2411-80	68	

Colours:

Mahogany
Saltbush
Slate Grey
Walnut

Note: Specifications subject to change without notice

www.futurewoodnz.co.nz
Industrial Plastic Shapes Ltd.
Tel: 9 442 4051 Fax: 9 442 4053